

Technical Data Sheet

EGYPELENE® TF540J

Polypropylene, Homopolymer

Product Description

EGYPELENE® TF540J is a polypropylene homopolymer nucleated grade for extrusion and thermoforming applications. EGYPELENE™ TF540J exhibits a good stiffness and transparency.

The main applications of EGYPELENE® TF540J are fruit baskets, trays, transparent drinking cups and containers.

Product Characteristics

Processing Methods

Thermoforming, extrusion.

Features

Homo polymer with good stiffness, transparency and good processability

Typical Customer Applications

Extrusion, Co-extrusion and thermoforming

Typical Properties	Normal Value	Units	Test Methods
Physical			
Melt flow	3.2	g/10 min	ISO 1133
Density	0.9	g/cc	ISO 1183
Mechanical			
Flexural Modulus	1550	Mpa	ISO 178
Tensile Stress at Yield, (23 °C, 50mm/min)	35	Mpa	ISO 527
Tensile Strain at Yield, (23 °C, 50mm/min)	10	%	ISO 527
Thermal			
Vicat Softening Temperature	154	°C	ISO 306

Regulatory Information

Egyptian Propylene & Polypropylene certifies that the above product is compliant with the USA FDA Code of Federal Regulations (CFR 21), Section 177.1520 (C) 1.1, and is suitable for use in articles that come into contact with food. Additionally, it is compliant with EU Regulation 10/2011 as amended.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally. In addition to any prohibitions of use specifically noted in this document, EPP may further prohibit or restrict the sale of its products into certain applications. For further information, please contact Egyptian Propylene & Polypropylene at info@epp-eg.com.